

Tech Data & Resources

R-VALUE (AGED)	6.0 at 1" thick 12.0 at 2" thick
DENSITY	1.75 lb/ft ³ (28 kg/m ³)
TACK-FREE TIME	30–60 seconds
CUTTABLE	2–5 minutes
FULLY CURED TIME	1 hour
CELL STRUCTURE	95% CLOSED cell content
FIRE RATING	ASTM E84 at 2" thick
Flame Spread	20
Smoke Developed	400
APPROVALS	GREENGUARD Gold ESR 2717 CCMC #13455-L NFPA 286
SHELF LIFE	6 months - Refill 12 months - Disposable