

## Tech Data & Resources

R-VALUE	4.5 at 1" thick
DENSITY	1.0 lb/ft <sup>3</sup> (16 kg/m <sup>3</sup> )
TACK-FREE TIME	approx. 5 minutes
CUTTABLE	<1 hour
FULLY CURED TIME	12–24 hours
CELL STRUCTURE	80% CLOSED cell content
FIRE RATING	ASTM E84/UL 723 Caulking & Sealant at ¾" bead
Flame Spread	25
Smoke Developed	50
APPROVALS	GREENGUARD Gold CCMC #13626-L
SHELF LIFE	12 months