

## Tech Data & Resources

R-VALUE	4.2 at 1" thick
DENSITY	Gun: 1.40 lb/ft <sup>3</sup> (17.6 kg/m <sup>3</sup> )
TACK-FREE TIME	approx. 5 minutes
CUTTABLE	<1 hour
FULLY CURED TIME	12–24 hours
CELL STRUCTURE	approx. 87% OPEN cell content
FIRE RATING	ASTM E84/UL 723 Caulking & Sealant at ¾" bead
Flame Spread	25
Smoke Developed	50
APPROVALS	GREENGUARD Gold AAMA 812: Complies with voluntary specs for low pressure window and door sealant
SHELF LIFE	15 months