

Spectrem® 4

Multi-Component, Neutral-Cure, Non-Staining Silicone Sealant

Product Description

Spectrem® 4-TS is a multi-component, neutral-cure, low-modulus silicone sealant that is non-staining and has low polar attraction to dirt. Spectrem 4-TS offers color flexibility with the opportunity to tint the material on site.

Basic Uses

Formulated for use in dynamically moving building joints with +/- 50% movement. Typical applications for Spectrem 4-TS include EIFS, expansion and control joints, tilt-up panel joints, precast concrete panel joints, and perimeter caulking (windows, doors, panels).

Features and Benefits

- Tremco Universal Color Paks in 70 standard colors and no minimum purchase quantity afford color flexibility for seamless façade appearance.
- Opportunity to tint materials on-site means quick turn-around.
- A 20-yr non-stain warranty when pre-approved and tested by Tremco in accordance with ASTM C1248.
- Low polar attraction to dirt makes buildings easier to clean and maintain.
- Low-modulus and low Shore A hardness reduces chance of EIFS substrate failures when compared to applications with medium-modulus sealants.
- · Primerless adhesion to most construction materials.
- Extended tooling time and workability in high temperatures.
- Ease of use reduces risk of application failure.
- No cure inhibition with Spectrem 1, Spectrem 2, Dymonic® FC when applied "wet-to-wet," minimizing the chance of leakage when sealants abut at glazing and other facade intersects.
- Low-VOC and zero-solvent content satisfies the LEED Indoor Environmental Criteria.
- Greenguard Gold certification ensures safety for use in the most sensitive indoor environments including hospitals and schools.

Availability

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

Colors

Spectrem 4-TS is available in 70 standard colors and can be custom matched to virtually any color upon request.

Limitations

- Do not apply over damp or contaminated surfaces.
- Not intended for continuous water immersion.
- Use with adequate ventilation.

Substrate Preparation

For good adhesion, the joint interface must be sound, clean and dry. Depending on the substrate, or presence of form release agents, masonry waterproofing, dust, loose mortar or laitance, architectural paints or finishes, the joint surface may require a thorough wire brushing, grinding, sandblasting, solvent washing and/or primer.

Applicable Standards

- Conforms to ASTM C920, Type M, Grade NS, Class 50, Use NT, G, M, A and O
- U.S. Federal Specification TT-S-00230, Class A
- U.S. Federal Specification TT-S-001543A Class A
- Canadian Standard CAN/CGSB-19.13-M87
- EIMA Test Method 300.01
- ASTM C 1382

Application

Mix in accordance with directions on the product container label. Mixing should continue until the desired uniform color is reached. Apply with conventional caulking equipment, filling the joint completely and tool.

Joint Design

May be used in any vertical or horizontal joint design in accordance with accepted architectural/engineering practice. Joint width should be 4-times anticipated movement, but not less than 1/4" (6 mm) wide.

Joint Backing

Closed-cell polyethylene backer rods are preferred as joint backing to control depth of sealant bead. Where depth of joint will prevent use of joint backing, an adhesive- backed polyethylene tape should be installed to prevent three-sided adhesion. Joint backing must be dry at time of sealant application.

Sealant Dimensions

For joint 1/4" (6 mm) to 1/2" (13 mm) wide, the width to depth ratio should be equal. Joints 1/2" (13 mm) wide or greater should have a sealant depth of 1/2" (13 mm). Minimum joint size is 1/4" x 1/4" (6 mm x 6 mm).

Clean Up

Tooling is recommended immediately after application to ensure firm, intimate contact with the joint interface. Dry tooling is preferred, although tooling agents can be utilized. Excess sealant and smears adjacent to the joint can be removed with IPA, MEK, Xylol or Toluol before sealant cures.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase price of the quantity of Tremco Products proven to be defective and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.


Spectrem® 4

Multi-Component, Neutral-Cure, Non-Staining Silicone Sealant

| TYPICAL PHYSICAL PROPERTIES | | |
|--|----------------|---|
| PROPERTY | TEST METHOD | TYPICAL VALUES |
| As Supplied: | | |
| Tack free time | ASTM C679 | 2 hr |
| Tooling Time | Skin Formation | 40 min |
| As Cured: After 14 days at 77 °F (25 °C), 50%RH | | |
| Joint Movement Capability Extension Compression | ASTM C719 | ±50% |
| Hardness (shore A) | ASTM C661 | 15 |
| Peel Strength Aluminum and Glass | ASTM C794 | 25 to 30 pli minimum -40 to +300 $^{\circ}\text{F}$ |
| Staining of Porous Substrates White Marble Primed & Unprimed | ASTM C1248 | No stain |
| Tear strength, die ("C") | ASTM D624 | 25 to 30 pli minimum |
| Tensile Strength at Max Elongation 100% Modulus | ASTM D412 | 110 to 130 psi 30 to 35 psi |

0316/SP4TSDS-ST

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.



3735 Green Rd Beachwood OH 44122 216.292.5000 / 800.321.7906 1451 Jacobson Ave Ashland OH 44805 419.289.2050 / 800.321.6357 220 Wicksteed Ave Toronto ON M4H1G7 416.421.3300 / 800.363.3213 1445 Rue de Coulomb Boucherville QC J4B 7L8 514.521.9555





